

1K BASECOAT 5100

A o	ne-component qui	ck drying acrylic basecoat for car and truck repair.
		quick drying basecoat with excellent adhesion and good flow
		ght fastness properties. Use our 2K Clearcoats after. Only for
	ional use.	
PLOLEBS	ionai use.	
Availab	le in solid, silve	er and pearl colours.
	Mixing ratio (by	100 % 1K Basecoat 5100
	volume), at 20°C	100 % 1K Basecoat Thinner Std
	Spray viscosity,	
\ s	DIN 4, at 20°C	16 - 20 s
	Application	1,3 - 1,5 mm
* *	method	2,5 - 3,5 bar
	Number of	2. Film thighnogg 40 60 um
T	spraycoats	2; Film thickness 40 - 60 μm
(1(1)	Flash off at 20°C	5 - 10 min
	Coverage	10 m ² /l (50 µm dry film thickness)
	Storage	Keep away from sources of ignition. Store separately from
	Shelf-life	flammable substances. Keep container tightly closed in a dry and well ventilated place.
	Shen-me	2,5 years
	REMARKS	Do not add more hardener than specified. Mix thoroughly.
	EQUIPMENT	Clean spray gun with a cleaning thinner
	CLEANING	
	SAFETY	Follow instructions of product label. For more information
		check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste
		Disposal.



1K BASECOAT 5100

TDS Version 2013_01

STORAGE	Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.
GUARANTEE	In unopened original packaging, 30 months from manufacturing date.
best knowledge. The use	supplied details and advises are based on our experiences and ar will be deemed to have satisfied himself independently of the duct for his own particular purpose. Guarantees cannot be claimed